

Level 0
0 - <10 min

Level 1
10 - 30 min

Level 2
30 - 60 min

Level 3
60 - 120 min

Level 4
120 - 240 min

Level 5
240 - 480 min

Level 6
< 480 min

SHIELDskin XTREME* Bright Latex 300 DI+



0120

EN374:2003



LEVEL 2

EN374:2003



- Category III PPE glove (PPE Directive 89/686/EEC)
- Complex Design - For mortal & irreversible risks
- Powder-free natural latex glove
- Ambidextrous
- 300 mm / 0.14 mm (EN 420:2003 + A1:2009)
- AQL 1.5 (EN 374-2:2014 Level 2)
- Viral penetration test (ISO 16604:2004 Procedure B & ASTM F1671-97b)
- Waterproof and for low chemical protection
- Tested for chemical permeation (EN 16523-1:2015 supersedes EN 374-3:2003)
- Typical particle levels: less than 900 per cm² more or equal 0.5µm
- Type I hypersensitivity & type IV hypersensitivity reduced

6 79-06-1 Acrylamide 40% ☉ 480'

6 1239-45-8 Ethidium bromide 5% ☉ 480'

6 7722-84-1 Hydrogen Peroxide, 12% ☉ 480'

6 7722-84-1 Hydrogen Peroxide, 30% ☉ 480'

6 7681-52-9 Sodium Hypochlorite 13% ☉ 480'

6 7664-93-9 Sulphuric acid 50% ☉ 480'

5 1310-73-2 Sodium Hydroxide, 40% ☉ 380'

3 67-68-5 Dimethyl Sulfoxide 99% (DMSO) ☉ 93'

2 7647-01-0 Hydrochloric Acid, 37% ☉ 44'

Level 0
0 - <10 min

Level 1
10 - 30 min

Level 2
30 - 60 min

Level 3
60 - 120 min

Level 4
120 - 240 min

Level 5
240 - 480 min

Level 6
< 480 min

SHIELDskin XTREME* Bright Latex 300 DI+

1	7697-37-2 Nitric Acid, 50%	⌚ 27'
1	7664-39-3 Hydrofluoric Acid, 48%	⌚ 26'
1	7664-39-3 Hydrogen Fluoride 48%	⌚ 26'
1	67-63-0 Isopropanol 70%	⌚ 14'
1	64-17-5 Ethanol, 70%	⌚ 13'
0	1336-21-6 Ammonium Hydroxide, 25%	⌚ 9'
0	67-63-0 Isopropanol 100%	⌚ 6'
0	64-17-5 Ethanol 100%	⌚ 4'
0	75-05-8 Acetonitrile 99,9%	⌚ 2'
0	67-64-1 Acetone 99.8%	⌚ 1'
0	67-56-1 Methanol 99,9%	⌚ 0'
0	1330-20-7 Xylene 98,5%	⌚ 0'