

Level 0
0 - <10 min

Level 1
10 - 30 min

Level 2
30 - 60 min

Level 3
60 - 120 min

Level 4
120 - 240 min

Level 5
240 - 480 min

Level 6
< 480 min

ecoSHIELD* Eco Nitrile PF 250




0120

EN374:2003



LEVEL 3

EN374:2003




- Category III PPE glove (PPE Directive 89/686/EEC)
- Complex Design - For mortal and irreversible risks
- Powder-free green/white nitrile glove
- Ambidextrous
- 250 mm / 0.10 mm (XL/10: 260 mm) (EN 420:2003 + A1:2009)
- AQL 0.65 (EN 374-2:2003 Level 3)
- Viral penetration test (ISO 16604:2004 Procedure B & ASTM F1671-97b)
- Waterproof and for low chemical protection
- Tested for chemical permeation (EN 16523-1:2015 supersedes EN 374-3:2003)
- Type I hypersensitivity eliminated - Type IV hypersensitivity reduced

6	10127-02-3 Acridine orange	⌚ 480'
6	79-06-1 Acrylamide 40%	⌚ 480'
6	66-81-9 Cycloheximide	⌚ 480'
6	1239-45-8 Ethidium bromide 5%	⌚ 480'
6	50-00-0 Formaldehyde, 37%	⌚ 480'
6	7722-84-1 Hydrogen Peroxide, 30%	⌚ 480'
6	Mixed Solution Mucocit®-T branded mixture	⌚ 480'
6	108-95-2 Phenol 0.1% solution	⌚ 480'
6	1310-58-3 Potassium Hydroxyde 40%	⌚ 480'



SHIELD Scientific
compliance comfort protection

CHEMICAL RESISTANCE GUIDE



ecoSHIELD* Eco Nitrile PF 250

6	127-09-3 Sodium acetate Sat. solution	⌚ 480'
6	1310-73-2 Sodium Hydroxide, 50%	⌚ 480'
6	7664-93-9 Sulphuric acid 50%	⌚ 480'
6	75-59-2 Tetramethylammonium hydroxide 2.5%	⌚ 480'
6	77-86-1 Tris (hydroxymethyl) aminomethane Sat. solution	⌚ 480'
4	7803-57-8 Hydrazine monohydrate 98%	⌚ 150'
3	7647-01-0 Hydrochloric Acid, 37%	⌚ 79'
2	108-87-2 Methylcyclohexane 99,9%	⌚ 55'
2	67-63-0 Isopropanol 70%	⌚ 45'
2	142-82-5 n-Heptane 99%	⌚ 41'
2	78-83-1 Isobutanol 99%	⌚ 39'
2	67-63-0 Isopropanol 100%	⌚ 35'
2	598-75-4 Secondary isoamyl alcohol 98%	⌚ 30'

Level 0
0 - <10 min

Level 1
10 - 30 min

Level 2
30 - 60 min

Level 3
60 - 120 min

Level 4
120 - 240 min

Level 5
240 - 480 min

Level 6
< 480 min

ecoSHIELD* Eco Nitrile PF 250

1	64-17-5 Ethanol, 70%	⌚ 22'
1	1336-21-6 Ammonium Hydroxide, 25%	⌚ 16'
1	108-95-2 Phenol 50%	⌚ 15'
1	64-17-5 Ethanol 100%	⌚ 11'
1	75-12-7 Formamide 99%	⌚ 11'
1	62-53-3 Aniline 99,9%	⌚ 10'
1	97-88-1 Butyl methacrylate 99,9%	⌚ 10'
1	67-68-5 Dimethyl Sulfoxide 99% (DMSO)	⌚ 10'
0	7664-39-3 Hydrofluoric Acid, 40%	⌚ 8'
0	64-19-7 Acetic Acid 100%	⌚ 4'
0	64-18-6 Formic acid 97.8%	⌚ 3'
0	1330-20-7 Xylene 98,5%	⌚ 2'
0	60-24-2 2-Mercaptoethanol 99%	⌚ 1'

Level 0
0 - <10 min

Level 1
10 - 30 min

Level 2
30 - 60 min

Level 3
60 - 120 min

Level 4
120 - 240 min

Level 5
240 - 480 min

Level 6
< 480 min

ecoSHIELD* Eco Nitrile PF 250

0	68-12-2 Dimethyl Formamide 99%	☉ 1'
0	67-64-1 Acetone 99.8%	☉ 0'
0	75-05-8 Acetonitrile 99,9%	☉ 0'
0	67-66-3 Chloroform 99,8%	☉ 0'
0	109-89-7 Diethylamine 99,5%	☉ 0'
0	141-78-6 Ethyl Acetate 100%	☉ 0'
0	64-18-6 Formic acid, 98,5 %	☉ 0'
0	67-56-1 Methanol 99,9%	☉ 0'
0	75-56-9 Propylene oxide 99%	☉ 0'