



White Nitrile 400 DI+

Powder Free Extra DI washed Ambidextrous Non-Sterile 40cm Nitrile Gloves

PPE Category III (Complex Design) according to Council Directive 89/686/EEC

Fully compliant to the latest PPE norms – EN 374:2003 “Protective gloves against chemicals and micro-organisms”

PRODUCT INFORMATION

Size	Catalogue Numbers	Applicable Norms with Pictograms		
Extra Small (XS/6)	69 8671	EN 374:2003	EN 374:2003	
Small (S/7)	69 8672			
Medium (M/8)	69 8673		Level 2	
Large (L/9)	69 8674			
Extra Large (XL/10)	69 8675	EN 420:2003 + A1:2009		
Extra Extra Large (XXL/11)	69 8676	Also meets or exceeds EN455-1: 2000, EN455-2:2009 + A2:2013, EN455-3:2015 & EN455-4:2009 relating to Council Directive 93/42/EEC for Medical Devices		

* SGS UK Ltd (Notified Body No: 0120), Unit 202B Worle Parkway, Weston-super-Mare, BS22 6WA, United Kingdom

Material: Synthetic soft nitrile polymer (Acrylonitrile Butadiene), based on Skin Nitrile™ technology. Contains no natural rubber latex.

Design: White, ambidextrous, beaded cuff plus textured palm and fingers.

Packaging: One hundred gloves (100) per inner poly bag. Packaging designed to comply with cleanroom environments processes. Gloves are flat-packed. Ten (10) poly bags per inner bag. Packed in a double-walled shipping case. 1000 gloves per case.

PHYSICAL PROPERTIES

Characteristics	Value	Test Method
Freedom from holes	1.5 AQL ¹	EN 374:2003

¹ AQL as defined per ISO 2859 for sampling by attributes

Tensile Properties	Tensile Strength (min) Typical		Ultimate Elongation	
- Before Aging	6.0N, min.	7.0N	500%, min.	EN 455-2:2015, ASTM D573-04(2015) and ASTM D 412-15a
- After Accelerated Aging	6.0N, min.	8.0N	400%, min.	

PHYSICAL PROPERTIES (Continued)

Characteristics	Value			Test Method
Dimensional	Measured Point	mm	mil	
- Nominal Thickness	Middle Finger	0.20	7.9	ASTM D3767-03(2014)
	Palm	0.15	6.0	
	Cuff	0.10	3.9	
- Length	385mm, min.	400mm, typical		EN420: 2003 + A1:2009

Palm Width

Nominal Width (mm)	XS/6	S/7	M/8	L/9	XL/10	XXL/11	EN 455-2:2015
	≤80	85	95	105	115	≥120	

Hand Circumference

Nominal Circumference (mm)	XS/6	S/7	M/8	L/9	XL/10	XXL/11	EN 420:2003 + A1:2009
	152	178	203	229	254	279	

CLEANLINESS PROPERTIES

Particles				Test Method
		Specification	Typical value	
Particles	Per cm ² ≥0.5µm	<1.200 particles	950 particles	IEST-RP-CC005.4

Extractables					Test Method	
Ion		Specification		Typical value		IEST-RP-CC005.4
Ammonium	NH ₄	0.100	ug/cm ²	0.030	ug/cm ²	
Bromide	Br	0.030	ug/cm ²	0.015	ug/cm ²	
Calcium	Ca	0.300	ug/cm ²	0.190	ug/cm ²	
Chloride	Cl	0.200	ug/cm ²	0.070	ug/cm ²	
Fluoride	F	0.010	ug/cm ²	0.005	ug/cm ²	
Magnesium	Mg	0.100	ug/cm ²	0.050	ug/cm ²	
Nitrate	NO ₃	0.200	ug/cm ²	0.100	ug/cm ²	
Potassium	K	0.100	ug/cm ²	0.050	ug/cm ²	
Sodium	Na	0.100	ug/cm ²	0.050	ug/cm ²	
Sulphate	SO ₄	0.100	ug/cm ²	0.050	ug/cm ²	
Nitrite	NO ₂	0.050	ug/cm ²	0.150	ug/cm ²	
Phosphate	PO ₄	0.050	ug/cm ²	0.030	ug/cm ²	

ADDITIONAL DATA

- **Biocompatibility** demonstrated by Modified Buehler and Primary Skin Irritation Tests.
- **Non detectable levels of chemical accelerators** using aqueous solution extraction (Phosphate buffered solution) and High Performance Liquid Chromatography (HPLC) assay method for quantitative analysis.
- **Free of Thiurams and Thiazoles** - these chemical accelerators are excluded from the manufacturing process.
- **Powder free** to minimize the potential consequences of powder-borne dermatitis. Residual powder content is 1.0 mg/glove (typical) with a limit of 2.0 mg/glove (ISO 21171:2006 "Medical gloves - Determination of removable surface powder").
- **Micro-organism and virus resistant** - micro-organism resistant per EN 374-2: 014 (Performance level 2, AQL <1.5 and inspection level G1 according to 1000ml water test) and passes viral penetration test using Phi-X 174 bacteriophage (ISO 16604:2004 Procedure B & ASTM F1671-97b).
- **FTIR**: non detectable levels of silicone, amide and DOP (IEST-RP-CC005.4).
- **Surface Resistivity**: $10^8 - 10^{10} \Omega/\text{sq}$. (ASTM D257-14).
- **NVR**: maximum 30mg/g (IEST-RP-CC005.4).
- **Tested for electrostatic properties** according to EN 1149-1/2/3 & 5.
- **Extensively tested for chemical permeation** according to EN 16523-1:2015 (please refer to chemical resistance guide on website - www.shieldscientific.com/public/chemical-resistance-guide).

QUALITY SYSTEMS

- Manufactured in accordance with ISO 9001:2015 and ISO 13485:2016.

“SHIELDskin™, A revolution in Glove Technology”



www.shieldscientific.com

SHIELDskin XTREME™ and Skin Nitrile™ are trade mark of SHIELD Scientific. © 2007 Copyright SHIELD Scientific B.V. All Rights reserved
Dr. Willem Dreeslaan 1 • 6721 ND Bennekom • The Netherlands - Phone +31 (0)317 700 202 • Fax +31 (0)318 503 742 • E-mail: Info@shieldscientific.com

V9 SHIELDskin XTREME™ White Nitrile 400 DI+ EN 07102016