

Level 0
0 - <10 min

Level 1
10 - 30 min

Level 2
30 - 60 min

Level 3
60 - 120 min

Level 4
120 - 240 min

Level 5
240 - 480 min

Level 6
< 480 min

SHIELDskin XTREME* Sterile Latex 330 DI+




0120

EN374:2003



LEVEL 3

EN374:2003



- Category III PPE glove (PPE Directive 89/686/EEC)
- Complex Design - For mortal & irreversible risks
- Powder-free natural latex glove
- Hand-specific
- 330 mm / 0.18 mm (EN 420:2003 + A1:2009)
- AQL 0.65 (EN 374-2:2014 Level 3)
- Viral penetration test (ISO 16604:2004 Procedure B & ASTM F1671-97b)
- Waterproof and for low chemical protection
- Tested for chemical permeation (EN 16523-1:2015 supersedes EN 374-3:2003)
- Typical particle levels: less than 950 per cm² more or equal 0.5µm
- Type I hypersensitivity & type IV hypersensitivity reduced

6	1239-45-8 Ethidium bromide 5%	⌚ 480'
6	7722-84-1 Hydrogen Peroxide, 12%	⌚ 480'
6	7722-84-1 Hydrogen Peroxide, 30%	⌚ 480'
6	1310-73-2 Sodium Hydroxide, 40%	⌚ 480'
6	7681-52-9 Sodium Hypochlorite 13%	⌚ 480'
6	7664-93-9 Sulphuric acid 50%	⌚ 480'
5	50-00-0 Formaldehyde, 37%	⌚ 379'
3	7647-01-0 Hydrochloric Acid, 37%	⌚ 84'
2	7664-93-9 Sulphuric acid 95%-98%	⌚ 33'

Level 0
0 - <10 min

Level 1
10 - 30 min

Level 2
30 - 60 min

Level 3
60 - 120 min

Level 4
120 - 240 min

Level 5
240 - 480 min

Level 6
< 480 min

SHIELDskin XTREME* Sterile Latex 330 DI+

1	67-63-0 Isopropanol 70%	⌚ 21'
1	1336-21-6 Ammonium Hydroxide, 25%	⌚ 14'
1	64-17-5 Ethanol, 70%	⌚ 13'
0	67-63-0 Isopropanol 100%	⌚ 7'
0	64-17-5 Ethanol 100%	⌚ 5'
0	75-05-8 Acetonitrile 99,9%	⌚ 3'
0	67-64-1 Acetone 99.8%	⌚ 2'
0	109-89-7 Diethylamine 99,5%	⌚ 1'
0	80-62-6 Methyl Methacrylate 99%	⌚ 1'
0	1330-20-7 Xylene 98,5%	⌚ 1'